

GUARDIAN SPECIFICATION SHEET - GWB61

APPLICATION OF GUARDIAN WATERBASED ANTI GRAFFITI COATING

(WATERBASED NON SACRIFICIAL COATING)

PREVIOUSLY PAINTED SURFACES

PREPARATION:

Determine the type and nature of existing paint before applying Guardian WB Anti Graffiti Coating. Check adhesion of existing painted surfaces, to ensure it is sound and fully bonded to substrate. If the old paint comes off it should be removed. Scrape off all loose and flaking paint, remove any existing graffiti with Guardian Graffiti Remover, wash vigorously with detergent, water and a stiff brush or high pressure clean. Mould and mildew should be removed and area high pressure water washed. Fill cracks etc. with a suitable 2 pack filler, sand all surfaces to a smooth flat finish and dust down. For sound surfaces previously painted with Guardian WB Anti Graffiti Coating sand back and dust off before product application. Freshly applied water based acrylic paint or acrylic render should be clean and dry.

THINNING Airless Spray Application No thinning required

Brush/roller application: Use 4-5mm nap Mohair roller. Apply Undiluted

RECOAT:

Airless Spray application: Wet on wet.

Brush/roller application: Between 3-4 hrs.

GUARDIAN SPECIFICATION GUIDE

SURFACE	PREPARATION	COATS	SYSTEM	DFT
IF PREVIOUS COATING IS WB GUARDIAN ANTI GRAFFITI COATING	- SAND BACK - DUST OFF - WIPE DOWN - CLEAN & DRY	1 1	GUARDIAN WB ANTI GRAFFITI COATING GUARDIAN WB ANTI GRAFFITI COATING	25 micron 25 micron
IF PREVIOUS COATING IS WATERBASED ACRYLIC	- DUST OFF - WIPE DOWN - CLEAN & DRY	1 1	GUARDIAN WB ANTI GRAFFITI COATING GUARDIAN WB ANTI GRAFFITI COATING	25 micron 25 micron
IF PREVIOUS COATING IS SOLVENT BASED ENAMEL/ALKYD	- SAND BACK - DUST OFF - WIPE DOWN - CLEAN & DRY	1 1	GUARDIAN WB ANTI GRAFFITI COATING GUARDIAN WB ANTI GRAFFITI COATING	25 micron 25 micron