

GUARDIAN SPECIFICATION SHEET - GWB62

APPLICATION OF GUARDIAN WB- WATERBASED ANTI GRAFFITI COATING

(WATERBASED NON SACRIFICIAL COATING)

BRICK - STONE - MASONRY

PREPARATION:

Remove any existing graffiti with Guardian Graffiti Remover. Wash down with detergent, water and a stiff brush or high pressure water clean to remove all loose material, (take care not to damage the mortar), allow to dry. Moisture to be less than 5%. Check the porosity of the substrate and the suitability of the substrate by applying a 1-2m2 test area prior to main application

APPLICATION:

Apply one light coat of Guardian Anti Graffiti Primer (20microns DFT max) and allow to dry 12-24hrs, followed by two even coats of Guardian Anti Graffiti Coating.

Brush/roller application: Use 4-5mm nap Mohair roller cover. Apply undiluted.

THINNING Airless Spray Application No thinning required

RECOAT:

Airless Spray application: Wet on Wet

Brush/roller application: 3-4 Hours

GUARDIAN SPECIFICATION GUIDE

SURFACE	PREPARATION	COATS		DFT
• BRICK, STONE, MASONRY	• REMOVE DIRT	1	GUARDIAN WB ANTI GRAFFITI PRIMER	20 micron
	• DUST OFF	1	GUARDIAN WB ANTI GRAFFITI COATING	25 micron
	• WIPE DOWN	1	GUARDIAN WB ANTI GRAFFITI COATING	25 micron
	• CLEAN & DRY			